



TECHNICAL DATA SHEET

PERFECTION FLOOR RESTORER /
R6090 (high gloss) , R6035 (satin)

DESCRIPTION

Saman Perfection Floor Restorer is a 100% acrylic finish recommended for hardwood, laminate and vinyl floors. It will provide a non-yellowing and durable finish, with the added benefits of low odor and fast drying time.

The Restorer enhances the appearance of the floor by adding a new protective layer (no build up). It removes scuff marks and restores sheen.

PRODUCT SPECIFICATIONS

pH: 7.5-8.0

Solids: 18 ± 1% (by weight); 16 ± 1% (by volume)

Viscosity: 13-19 seconds (Zahn cup #2)

Density: 1.01-1.03 kg/l

Drying times: approximately 1 hour at 70°F and 50% relative humidity. Drying time may vary according to room temperature and relative humidity.

Coverage: 250 sq. ft/l

VOC: 161 g/l

Gloss levels: gloss = 90%, satin = 40-45% (measured at an angle of 60° or 85°)

Recommended applicators: pad applicator or microfiber mop

Clean up: Clean applicator and equipment with water.

Storage: minimum temperature 41°F, maximum temperature 95°F. Freeze-thaw stable (if frozen, thaw completely before using). KEEP OUT OF REACH OF CHILDREN.

Shelf life: at least 1 year in a well closed container.

APPLICATION

CAUTION: Do not apply the Restorer on a floor that has been oiled or waxed.

1. Remove furniture and rugs. Sweep or vacuum all dust.
2. Thoroughly clean the floor with Saman Perfection Adhesion Improver cleaner. Allow the floor to dry.

Allow the Restorer to reach room temperature before application. Apply the product at room temperature between 60 and 80 °F with a relative humidity rate between 30 and 80%.

1. Well mix the Restorer by shaking vigorously the bottle during 1 minute.
2. Pour a small amount of Restorer on the floor and spread evenly with the applicator. Work in sections small enough to keep the applicator pad wet. When the entire floor is finished, immediately rinse the applicator pad with water. For a glossier floor, a 2nd coat of Refinisher may be applied after 4 hours.
3. Allow to dry at least 4 hours before walking on the floor. Wait 24 hours before allowing heavy traffic.

To the best of our knowledge, the information contained herein is accurate. Since conditions and methods are beyond our control, no warranty is expressed or implied as for the final result. The user is advised to access the suitability of the product on a test area before application.